

**ALLOY**  
**DATA**



# MECHANICAL AND PHYSICAL PROPERTIES OF Alloy C42520

Olin Alloy C4252 is a dispersion and solid solution strengthened alloy developed for use in the electronic and automotive connector market. It was developed to provide a cost-effective solution to the increasing price pressures placed upon connector manufacturers using traditional phosphor bronze alloys. Its unique combination of properties provides higher current carrying capacity than Alloy C510 at the same strength. For more information contact Olin Market Development Engineering at 618-258-5255, OlinBrass.com or email us at [info@olinbrass.com](mailto:info@olinbrass.com).

**Table 1  
Composition Limits of C4252**

<b>Copper<sup>1</sup></b>	<b>88.0-91.0%</b>
<b>Tin</b>	<b>1.5-3.0%</b>
<b>Iron</b>	<b>0.05-0.20%</b>
<b>Nickel</b>	<b>0.05-0.20%</b>
<b>Phosphorus</b>	<b>0.01-0.20%</b>
.....	
<b>Zinc</b>	<b>Remainder</b>
<b>Lead</b>	<b>0.05% Max.</b>

1. Cu plus Named Elements, 99.7% min.




Figure 1: Strength vs Conductivity for three connector alloys.

**Table 2  
Physical Properties of C4252**

	English Units	Metric Units
Density	0.318 lb/in <sup>3</sup> @ 68°F	8.80 gm/cm <sup>3</sup> @ 20°C
Thermal Conductivity	70 Btu-ft/ft <sup>2</sup> -hr-°F @ 68°F	120 W/mK cal-cm/cm <sup>2</sup> -sec-°C @ 20°C
Electrical Resistivity	34.57 ohm circ mils/ft @ 68°F	5.75 microhm-cm @ 20°C
Electrical Conductivity (Annealed)	30% I.A.C.S. † @ 68°F	17 MS/m Megmho/cm @ 20°C
Modulus of Elasticity	16,000,000 psi	110 kN/mm <sup>2</sup>
Coefficient of Thermal Expansion 68-572°F (20-300°C)	10.2 PPM/°F	18.4 PPM/°C

† International Annealed Copper Standard

**Table 3  
Mechanical Properties of C4252**

Temper	Tensile Strength		Nominal Yield Strength (0.2% Offset)		Nominal % Elong. in 2 Inch (51mm)	90° Bend Formability GW/BW <sup>2,3</sup>
	ksi	N/mm <sup>2</sup>	ksi	N/mm <sup>2</sup>		
1/2 Hard	58 – 73	400 – 505	60	415	20	0.0/0.0
3/4 Hard	68 – 79	470 – 545	71	490	15	0.0/0.0
Hard	76 – 91	525 – 625	81	560	10	0.0/0.5
Ex. Hard	88 – 103	605 – 710	92	635	6	0.5/1.8
Spring	95 – 110	655 – 760	100	690	4	1.0/3.0
Ex. Spring	100 – 114	690 – 785	103	710	3	

2. R/T = Bend Radius/Material Thickness @ <0.012" (0.3mm) thick 11/16 inch (17.5mm) wide.  
3. Relief annealed product recommended for maximum formability.

<b>MAIN OFFICE and MILL</b> Olin Brass 427 North Shamrock Street East Alton, Illinois 62024-1197 Phone: 618-258-5255 Fax: 618-258-5772	<b>OLIN ASIA PACIFIC</b> 1 Kim Seng Promenade Great World City, East Tower #13-04 Singapore 237994 Phone: 65.6238.1155 Fax: 65.6238.0660	<b>OLIN BRASS JAPAN</b> 145-1 Tokiwa-cho Hamamatsu-shi, Shizuoka-ken 430-0917 Japan Phone: 81.53.413.1500 Fax: 81.53.451.0010	<b>OLIN CHINA</b> Room 2004, Aetna Tower No. 107 Zunyi Road Shanghai 200051, CHINA Phone: 86.21.6237.5898 Fax: 86.21.6237.5805
---	---	--	---

**OLIN BRASS – HEADQUARTERS  
OFFICE AND MILL**

427 North Shamrock Street  
East Alton, Illinois 62024-1197  
Phone: 618-258-5255  
Fax: 618-258-2769

**WATERBURY ROLLING MILLS, INC.  
OFFICE AND MILL**

240 East Aurora Street  
Waterbury, Connecticut 06708  
Phone: 203-754-0151  
Fax: 203-754-1016

**BRYAN METALS INC.  
OFFICE AND MILL**

1103 South Main Street  
Bryan, Ohio 43506-0487  
Phone: 419-636-4571  
Fax: 419-636-3994

**SOMERS THIN STRIP  
OFFICE AND MILL**

215 Piedmont Street  
Waterbury, Connecticut 06706  
Phone: 203-597-5000  
Fax: 203-597-5081

**NEW HAVEN COPPER CO.  
OFFICE AND MILL**

79 Main Street  
Seymour, Connecticut 06483

**INTERNATIONAL SALES OFFICES AND FACILITIES**

**OLIN ASIA PACIFIC**

1 Kim Seng Road Promenade  
Great World City, East Tower #13-04  
Singapore 237994  
Phone: 65.6238.1155  
Fax: 65.6238.0660

**OLIN BRASS JAPAN**

Hamamatsu MH Bldg 13F  
145-1 Tokiwa-cho  
Hamamatsu-shi, Shizuoka-ken  
430-0917 Japan  
Phone: 81.53.413.1500  
Fax: 81.53.451.0010

**OLIN SHANGHAI**

Room 2004, Aetna Tower  
No. 107 Zunyi Road  
Shanghai 200051, CHINA  
Phone: 86.21.6237.5898  
Fax: 86.21.6237.5805

**OLIN LOUTONG METALS (GZ) LTD. CO.**

No. 8 Jun Gong Lu, East District  
Guangzhou Economic Technological & Dev. District  
Guangzhou, P.R. China 510530  
Phone: 86.20.8226.6818  
Fax: 86.20.8226.6718

**OLIN APPROVED INTERNATIONAL DISTRIBUTORS**

**UNITED KINGDOM / IRELAND**

**EIP Metals Limited**

Heath Street South  
Birmingham B18 7PZ  
Phone: 44 (0) 121 452 1199  
Fax: 44 (0) 121 456 1595  
E-mail: [sales@eipmetals.co.uk](mailto:sales@eipmetals.co.uk)  
Website [www.eipmetals.co.uk](http://www.eipmetals.co.uk)

**EUROPE**

**Walter Türkis GmbH**

Struthstrasse 35  
55743 Idar-Oberstein  
Germany  
Phone: 49 (0) 6781 62-0  
Fax: 49 (0) 6781 62-28  
E-mail: [service@tuerkis-schneid-center.de](mailto:service@tuerkis-schneid-center.de)  
Website [www.tuerkis-schneid-center.de](http://www.tuerkis-schneid-center.de)

