

Known as Gilding Metal, C210 is well known for its historic use in the "penny". This versatile, low-cost alloy is often the choice of engineers for applications including deep drawn parts such as bullet jackets and coined products. The combination of moderate conductivity and improved strength make C210 a valuable option for electrical applications where performance requirements preclude the use of standard cooper. For more information contact Olin Brass Market Development Engineering at 618-258-5255, OlinBrass.com or email us at info@olinbrass.com.

Chemical Composition	
Copper¹	94.0-96.0%
Zinc	Remainder
Lead	0.05% Max
Iron	0.05% Max

¹ Copper plus named elements, 99.8%




Figure 1: Comparison of Yield Strength and Electrical Conductivity performance of select Hard temper brass materials.

Physical Properties

	English Units	Metric Units
Density	0.320 lb/in ³ @ 68°F	8.86 g/cm ³
Thermal Conductivity	135 BTU-ft/ft ² -hr-°F	233 W/mK
Electrical Resistivity	18.5 ohm circ mils/ft	3.08 microhm-cm
Electrical Conductivity (annealed)	56% IACS*	0.325 megamho/cm
Modulus of Elasticity	17,000,000 psi	117 kN/mm ²
Coeff. Of Thermal Expansion		
68-572°F (20-300°C)	10.0 PPM/°F	18.1 PPM/°C

*International Annealed Copper Standard

Mechanical Properties

Temper ¹	Tensile Strength		Yield Strength		% Elongation ²	Typical 90° Bend Formability GW/BW ³	
	ksi	N/mm ²	ksi	N/mm ²			
Annealed (Soft) ⁴	34-40	235-275	10	70	45	-	-
1/4 Hard	37-47	255-325	30	205	30	-	-
1/2 Hard	42-52	290-360	44	305	17	-	-
3/4 Hard	46-56	315-385	50	345	9	-	-
Hard	50-59	345-405	53	365	5	-	0.5
Extra Hard	56-64	385-440	59	405	2 Max	0.5	1.0
Spring	60-68	415-470	63	435	2 Max	1.0	1.8
Extra Spring	61-69	420-475	64	440	2 Max		

¹ Mechanical properties subject to change. All rolled- tempers are accepted or rejected based on Tensile Strength.

² Nominal Values in 2" (51mm)

³ DATA FOR REFERENCE ONLY. R/T = Bend Radius/Material Thickness <0.016" (0.4mm) thick, 11/16 (17.5mm) wide.

⁴ Annealed temper are manufactured to a grain size only, consult mill for additional info.

Olin Brass Headquarters

4801 Olympia Park
Plaza, Suite 3500
Louisville, KY 40241
Ph: 502-873-3000

GBC METALS ASIA PACIFIC PTE LTD

1 Kim Seng Promenade
Great World City, E Tower
Singapore 237994
Ph: 65.6238.1155

GBC METALS LLC SHANGHAI

Room 2004 Aetna Tower
No. 107 Zunyi Rd
Shanghai 200051 China
Ph: 86.21.6237.5898

OLIN BRASS-HEADQUARTERS

4801 Olympia Park
Plaza, Suite 3500
Louisville, KY 40241
Ph: 502-873-3000

OLIN BRASS - MILL

285 Lewis & Clark Blvd.
East Alton, IL 62024
Ph: 618-258-5255

BRYAN METALS INC.

1103 South Main Street
Bryan OH 43506-0487
Ph: 419-636-4571
Fx: 419-636-3994

SOMERS THIN STRIP

215 Piedmont Street
Waterbury, CT 06706
Ph: 203-597-5000
Fx: 203-597-5081

A.J. OSTER COMPANY

180 ALEXANDRA WAY
Carol Stream, IL 60188-2068
Ph: 630-260-1040
Ph: 800-323-9644
Fx: 630-260-1102

A.J. OSTER CARIBE, INC.

Centro industrial Rio Canas
Lote 29, P.M.B HC-01
Box 29030
Caguas, PR 00725
Ph: 787-747-7575

A.J. OSTER FOILS, INC.

2081 McCrea Street
Alliance, OH 44601-2793
Ph: 330-823-1700
Ph: 800-321-9750
Fx: 330-823-1705

A.J. OSTER WEST INC.

22833 La Palma Avenue
Yorba Linda, CA 92887-4767
Ph: 714-692-1000
Ph: 800-933-5933
Fx: 714-692-1225

A.J. OSTER COMPANY

457 Industrial Drive
Warwick, RI 02886
Ph: 401-739-0800
Fx: 401-739-1276

INTERNATIONAL SALES OFFICES & FACILITIES**GBC METALS ASIA PACIFIC PTE LTD.**

1 Kim Seng Road Promenade
Great World City, East Tower #13-04
Singapore 237994
Ph: 65.6238.1155
Fx: 65.6238.0660

GBC METALS LLC SHANGHAI

Room 2004, Aetna Tower
No. 107 Zunyi Road
Shanghai 200051, China
Ph: 86.21.6237.5898
Fx: 86.21.6237.5805

OLIN LUOTONG METALS (GZ) Co Ltd

No. 8 Jung Gong Road, East District
Guangzhou Economic Technological & Dev District
Guangzhou, P.R. China 510530
Ph: 86.20.8226.6818
Fx: 86.20.8226.6718

DOWA-OLIN METAL CORPORATION

2630, Shingai
Iwata-shi, Shiznoka-ken
438, Japan
Ph: 81.538.37.5111
Fx: 81.538.37.0147

OLIN BRASS - INTERNATIONAL DISTRIBUTORS**UNITED KINGDOM / IRELAND****Aurubis UK Ltd.**

Rabone Park, Smethwick
West Midlands B66 2NN
England
Ph: 44 (0) 121 555 1199
Fx: 44 (0) 121 555 1188
Email: info-uk@aurubis.com
Website: www.aurubis.com

EUROPE**Walter Türkis GmbH**

Struthstrasse 35
55743 Idar-Oberstein
Germany
Ph: 49 (0) 6781 62-0
Fx: 49 (0) 6781 62-28
Email: service@tuerkis-schneid-center.de
Website: www.tuerkis-schneid-center.de

OLIN BRASS MEXICO S.A. de CV

Av. La Griega # 117
Parque Industrial Queretaro
Santa Rosa, Jaurgui
Queretaro, Mexico 76220
Ph: 52 442 2 29 40 00
Fx: 52 442 2 29 40 29